

Dynacoat Filler 4100 (Sanding version)

A white, black and grey colored two pack, voc compliant high build sanding filler with very good sanding and filling properties.

**MIXING RATIO**

4 Dynacoat Filler 4100
1 Dynacoat Filler 4100 Hardener
10% Dynacoat Thinner (optional)

**MIXING STICK**

Use Dynacoat mixing stick D13


**EQUIPMENT**

Spray gun set-up: 1.6-2.0 mm
Application pressure: 1.7-2.2 bar at the air inlet*

*See user manual spray gun

**APPLICATION**

1-3 x 1 coat

**FLASH-OFF**

5-10 minutes between coats
5-10 minutes before bake

**DRYING**

3-4 hours at 20°C
30-40 minutes at 60°C

**RECOATABLE WITH**

All topcoats

**PROTECTION**

Use suitable respiratory protection. AkzoNobel Vehicle Refinishes recommends the use of a fresh air supply respirator.

Dynacoat Filler 4100 (non sanding version)

A white, black and grey colored two pack filler with good filling properties.

This product is not for sale to vehicle refinishers in the EU, who need to comply with the Directive 2004/42/EC

**MIXING RATIO**

- 4 Dynacoat Filler 4100
- 1 Dynacoat Filler 4100 Hardener
- 1 Dynacoat Thinner

**MIXING STICK**

Use Dynacoat mixing stick D14

**EQUIPMENT**

Spray gun set-up: 1.2-1.4 mm
Application pressure: 1.7-2.2 bar at the air inlet*

*See user manual spray gun

**APPLICATION**

1-2 x 1 coat

**FLASH-OFF**

10-15 min between coats
15-20 min before recoating

**RECOATABLE**

All topcoats

**PROTECTION**

Use suitable respiratory protection. AkzoNobel Vehicle Refinishes recommends the use of a fresh air supply respirator.

PRODUCT AND ADDITIVES	Dynacoat Filler 4100 Dynacoat Filler 4100 Hardener Dynacoat Thinner Fast Dynacoat Thinner Medium Dynacoat Thinner Slow	
BASIC RAW MATERIALS	Filler:	acrylic resin
	Hardener:	poly-isocyanate resin
SUITABLE SUBSTRATES	Existing finishes, including thermoplastic acrylic finishes Steel Washprimer 1K Plastics Primer Polyester Putties 2K Epoxy Primer	
SURFACE PREPARATION	Existing finishes: Degrease and sand with P220-P320 dry or P400-P600 wet Polyester Putties: Sand with P220-P320 dry Steel surfaces: Degrease and sand with P220-P320 dry	
MIXING	Sanding version 4 Dynacoat Filler 4100 1 Dynacoat Filler 4100 Hardener 10% Dynacoat Thinner (optional) Use mixing stick D13 Non sanding version 4 Dynacoat Filler 4100 1 Dynacoat Filler 4100 Hardener 1 Dynacoat Thinners Fast / Medium / Slow	
VISCOSITY	Sanding:	20-24 seconds at 20°C
	Non sanding:	16-18 seconds at 20°C
POTLIFE	Sanding:	60 minutes at 20°C
	Non sanding:	90 minutes at 20°C
SPRAY GUN FLUID TIP AND WORKING PRESSURE	Sanding Spray gun: Gravity feed:	Fluid tip: 1.6 – 2.0 mm
	Non sanding Spray gun: Gravity feed:	Fluid tip: 1.2 – 1.4 mm
		Pressure: 1.7 – 2.2 bar (see user manual spray gun) HVLP max 0.7 at aircap
		Pressure: 1.7 – 2.2 bar (see user manual spray gun) HVLP max 0.7 at aircap

APPLICATION**Sanding**

Apply 1-3 single coats, allowing for 5 to 10 minutes flash off time between coats. If force dried, allow for a minimum flash-off time of 5-10 minutes before bake.

Non sanding

Apply 1-2 single flowing coats, allow 10-15 minutes flash off between coats

CLEANING OF EQUIPMENT

Use Dynacoat Guncleaner

FILM THICKNESS

Sanding: 40-50 µm per coat
Non sanding: 20-25 µm per coat

DRYING**Dry to sand**

Sanding
Non sanding

20°C

3-4 hours
1.5 hours

60°C

30-40 minutes
30 minutes

Denibbing

20 min

Infra red short wave

Half power
4 minutes

Full power
15 minutes

RECOMMENDED SAND PAPER

P400-P500 for dry sanding
P800-P1000 for wet sanding

RECOAT TIME**Non sanding**

Allow for a minimum of 20 minutes flash-off time at 20°C before recoating.
Apply topcoat within 6 hours at 20°C

RECOATABILITY

Dynacoat basecoats and topcoats

PRODUCT STORAGE

Product shelf-life is determined when products are stored unopened at 20°C.
Avoid extreme temperature fluctuation.

SHELF LIFE

2 years at 20°C

VOC**Sanding version****2004/42/IIB(c)(540)540**

The EU limit value for this product (product category: IIB.c) in ready to use form is max. 540 g/liter VOC.

The VOC content of this product (sanding version) in ready to use form is max. 540 g/liter.

Non sanding version

The VOC content of the non-sanding version in ready to use form is max. 601 g/liter.

Akzo Nobel Car Refinishes B.V.
Address: Rijksweg 31, PO Box 3, 2170 BA Sassenheim
Tel: +31(0)71308-6944

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE: The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Coatings brand names mentioned in this data sheet are trademarks of or are licensed to Akzo Nobel.

Head Office

Akzo Nobel Car Refinishes B.V., PO Box 3, 2170 BA Sassenheim, The Netherlands. www.dynacoat.com